


Felite™ Resin

FA201-U



Strong Base Anion, Macroporous

Uniform Mesh Size

Cl⁻ form

Industrial Grade

Felite™ FA201-U is a highly efficient and durable, Type I macroporous strong base anion exchange resin with quaternary ammonium as the functional group. Its macroporous structure provides high operating capacity and excellent regeneration efficiency and allows complete removal of all anions, including weakly dissociated ions such as silica. Its uniform mesh beads distribution provides minimal pressure loss and better regeneration efficiency.

Felite™ FA201-U resin can be used as an organic scavenger placed in front of a deionization system. Working in the chloride form, it removes the natural organic substances from the raw water, protecting subsequent anion exchange resins from possible irreversible organic fouling. Felite™ FA201-U is especially well suited for high flow rate and high-temperature polishing applications.

Principal Application:

- Deminceralization;
- Mixed Bed Anion Component;
- Organic scavenger;

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Styrene/DVB, Macroporous
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic form, as shipped	Cl ⁻
Total Capacity (mmol/ml)	1.15 min. (Cl ⁻)
Moisture Retention	57 -63%
Particle Size Range (mm)	0.4 - 0.8 (≤0.4mm, 1% max.; > 0.9mm, 5% max.)
Uniformity Coefficient (max.)	1.25
Reversible Swelling, Cl⁻ → OH⁻ (max.)	20%
Shipping Weight (g/L, approx.)	640 - 690 (41 lb/ft ³)
Specific Gravity	1.08
Temperature Limit	100°C (212 °F)
Stability, pH Range	0 - 14

PACKAGING:



25 Litres / 1 cu.ft PE Bag;
42 Bags Per Pallet;
20 Pallets Per 20ft Container



1 m³ Supersack Per Pallet;
20 Pallets Per 20ft Container



Asia Pacific

Yancheng, Jiangsu, China
sales@felitecn.com

America


San Gabriel, CA, USA
sales@felitecn.com

Europe


Cluj Napoca, Romania
sales@felitecn.com



PRESSURE DROP



BACKWASH EXPANSION



PERFORMANCE

The operating capacity depends on several factors such as the water analysis and the level of regeneration. The data to calculate the operating capacity and the ionic leakage with co-flow regeneration are given in the Engineering Data Sheets.

LIMITS OF USE

Felite™ FA201 resin is suitable for industrial uses. For other specific applications such as pharmaceutical, food processing or potable water applications, it is recommended that all potential users seek advice from Felite™ Resin Technology in order to determine the best resin choice and optimum operating conditions.

HYDRAULIC CHARACTERISTICS

Figure 1 shows the pressure drop data for Felite™ FA201 resin, as a function of service flow rate and water temperature. Figure 2 shows the bed expansion of Felite™ FA201 resin, as a function of backwash flow rate and water temperature. Pressure drop data are valid at the start of the service run with clear water and a correctly classified bed.

SUGGESTED OPERATING CONDITIONS:

Minimum Bed Depth

700mm

Service Flow Rate

Up to 120 BV*/h

Regeneration

- **Regenerant**

NaOH

- **Level (g/L)**

50 - 150

- **Concentration (%)**

2 - 4

- **Flow Rate (BV/h)**

4 - 6

- **Minimum Contact Time**

30 minutes

- **Slow Rinse**

2 BV* at regeneration flow rate

- **Fast Rinse**

4 - 8 BV* at service flow rate

* 1 BV (Bed Volume) = 1 m³ solution per m³ resin

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Felite™ expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.

Asia Pacific

Yancheng, Jiangsu, China
sales@felitecn.com

America

San Gabriel, CA, USA
sales@felitecn.com

Europe

Cluj Napoca, Romania
sales@felitecn.com

**Felite™
Resin
Technology**