


# Felite™ Resin

## FC110-C



Strong Acid Cation, Gel

Coarse Mesh Size

Na<sup>+</sup> form

Industrial Grade

Felite™ FC110-C is a 10% crosslinked gel strong acid cation resin with a coarse mesh range, supplied in sodium form.

Profiting from its low surface area and high void volume, Felite™ FC110-C is excellent for use in high flow rate applications where the lowest possible pressure loss and the highest possible flow rate are needed.

### Principal Application:

- Softening – Industrial;
- Softening – High Temperature;
- Softening – High Flow Rate;
- Demineralization;

### TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

<b>Polymer Structure</b>	Styrene/DVB, Gel
<b>Appearance</b>	Spherical Beads
<b>Functional Group</b>	Sulfonic Acid
<b>Ionic form, as shipped</b>	Na <sup>+</sup>
<b>Total Capacity (mmol/ml)</b>	2.2 min. (Na <sup>+</sup> )
<b>Moisture Retention</b>	40 - 43%
<b>Particle Size Range (mm)</b>	0.6 - 1.2 (≤0.6mm, 1% max.; > 1.2mm, 5% max.)
<b>Uniformity Coefficient (max.)</b>	1.4
<b>Reversible Swelling, Na<sup>+</sup> → H<sup>+</sup> (max.)</b>	8%
<b>Shipping Weight (g/L, approx.)</b>	820 - 860 (54 lb/ft <sup>3</sup> )
<b>Specific Gravity</b>	1.30
<b>Temperature Limit</b>	130°C (265°F)
<b>Stability, pH Range</b>	0 - 14

### PACKAGING:



25 Litres / 1 cu.ft PE Bag;  
48 / 42 Bags Per Pallet;  
20 Pallets Per 20ft Container



1 m<sup>3</sup> Supersack Per Pallet;  
20 Pallets Per 20ft Container



#### Asia Pacific

Yancheng, Jiangsu, China  
sales@felitecn.com

#### America

San Gabriel, CA, USA  
sales@felitecn.com

#### Europe


Cluj Napoca, Romania  
sales@felitecn.com



## PRESSURE DROP



## BACKWASH EXPANSION



## PERFORMANCE

The operating capacity depends on several factors such as the water analysis and the level of regeneration. The data to calculate the operating capacity and the ionic leakage with co-flow regeneration are given in the Engineering Data Sheets.

## LIMITS OF USE

Felite™ FC110 resin is suitable for industrial uses. For other specific applications such as pharmaceutical, food processing or potable water applications, it is recommended that all potential users seek advice from Felite™ Resin Technology in order to determine the best resin choice and optimum operating conditions.

## HYDRAULIC CHARACTERISTICS

Figure 1 shows the pressure drop data for Felite™ FC110 resin, as a function of service flow rate and water temperature. Figure 2 shows the bed expansion of Felite™ FC110 resin, as a function of backwash flow rate and water temperature. Pressure drop data are valid at the start of the service run with clear water and a correctly classified bed.

## SUGGESTED OPERATING CONDITIONS:

<b>Minimum Bed Depth</b>	700mm		
<b>Service Flow Rate</b>	5 - 40 BV*/h		
<b>Regeneration</b>			
- Regenerant	HCl	H <sub>2</sub> SO <sub>4</sub>	NaCl
- Level (g/L)	50 - 150	60 - 240	80 - 250
- Concentration (%)	5 - 8	0.7 - 6	10
- Flow Rate (BV/h)	2 - 5	2 - 20	2 - 8
- Minimum Contact Time	30 minutes		
- Slow Rinse	2 BV* at regeneration flow rate		
- Fast Rinse	2 - 4 BV* at service flow rate		

\* 1 BV (Bed Volume) = 1 m<sup>3</sup> solution per m<sup>3</sup> resin

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Felite™ expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.

### Asia Pacific

Yancheng, Jiangsu, China  
sales@felitecn.com

### America

San Gabriel, CA, USA  
sales@felitecn.com

### Europe

Cluj Napoca, Romania  
sales@felitecn.com

